

MAIN PRODUCT- PROPERTIES

- High-gloss 2-pack PUR Topcoat for nominal dry film thickness 50 µm
- Typical application areas: building machines, ACE, mobile cranes with high optical demands
- Distinguished light stability at natural weathering
- Can be painted wet-on-wet after 15 minutes in combination with WIEREGEN-C0077-Metallgrund (max. wet film thickness 75 µm)

PRODUCT DATA

WIEREGEN-M77N, high-gloss



M77N-H.... (RAL-colours, other on request)



Mixing ratio by weight

2:1 with curing agent DX-77N



Thinner V-77N (standard)
Thinner V-78 (fast: ambient temperature 10 to 20 °C)

WIEREGEN-M77N / Guideline

	Density (g/mL)	Solid content (weight %)	VOC-content (weight %)	Solid content by volume	
	1.20	77.5	22.5	(%)	(mL/kg)
				69.0	575
	DFT * (µm)	Calculated wet-film thickness (µm)	Consumption (kg/m²)	Spreading rate (m²/kg)	
	50	69	0.090	11.1	

COMMENTS ON PROCESSING

Recommendation at
temperatures
of approx. 20 °C



Airmix



**High
pressure**



**Roller/Brush
application**




Application viscosity (s) (4 mm DIN-cup)	18 to 22	20 to 25	35 to 45
Nozzle diameter (mm) Spraying angle (degree)	0.23 40 to 60	1.2 to 1.5	-
Material pressure (bar)	100 to 120	-	-
Atomiser pressure (bar)	2.5 to 3.5	3.0 to 5.0	-
DFT* per working operation (µm)	30 to 50	30 to 50	30 to 50
Addition of thinner (%)	8 to 12	6 to 10	0 to 2



Pot life

1 to 2 hours (relating to temperature)

* DFT = Dry Film Thickness

Drying/Curing times at 50 µm DFT with thinner V-77N		Ambient air temperature 20 °C
	touch dry:	after 60 to 90 minutes
	tack free:	after 6 to 8 hours
	ready for overcoating/handable:	after 24 hours

INSTRUCTIONS FOR APPLICATION

Surface preparation

Required Priming coats (see below)

- Remove adhesion-reducing substances e. g. cleaning, washing
- Before overcoating of other priming coats compatibility tests are recommended



Air and surface temperature

optimal at 15 to 25 °C, not below 10 °C, not over 40 °C



max. 80 % relative humidity

PAINT SYSTEMS

EXAMPLES

		Product(s) (other paint systems on request)
	Priming coats	WIEREGEN-C0077-Metallgrund WIEREGEN-M77N-Metallgrund GEHOPON-E44R-Metallgrund
	Top coat	WIEREGEN-M77N

SAFETY MEASURES



The relevant data can be found in the current material safety data sheets, available at www.geholit-wierner.de.

The statements made here are based on the present state of our knowledge. We do not assume liability for damages resulting from the use of the material or from any advice given by our employees. In this respect, any advice given by our employees has to be seen as not binding. The processor is responsible for the supervision or construction, the maintaining of process guidelines and the observation of the established rules of techniques, even if our employees are present at the time our material is being applied. This information is subject to modifications due to technical improvements. The latest edition of this information replaces all previous issues.